

塗料粘度カップ換算表

DIN cup No.4と各種塗料粘度カップの換算表です。単位は20°C/秒。

DIN No.4	IWATA	FORD No.4	BS No.4	BS ISO No.4
14	11	13	17	23
15	13	14	18	27
16	15	16	20	32
17	16	17	23	36
18	17	18	25	41
19	18	20	27	45
20	20	21	28	49
21	22	23	30	54
22	23	24	32	57
23	25	26	34	61
24	26	28	36	66
25	27	29	38	72
26	28	31	40	74
27	31	32	42	78